





Origin® Materials

Overview of the materials portfolio for P3™ DLP technology with guidance to determine the appropriate material for your application need.





Origin® Preferred Materials Overview

forward**am**



Preferred, Validated and Open Materials

Origin® users can use a broad range of high-performance materials on their printer. They can choose from three different material categories: Preferred, Validated and Open.

Origin Preferred Materials go through more advanced testing than Validated Materials to achieve:

- Better and repeatable accuracy targets
- First print success rate
- Application-specific profiles
- Relevant certification test results

All Preferred Materials are sold by Stratasys whereas Validated and Open materials may not be.

The following pages show Stratasys Preferred Materials presented by functionality type for easy selection:

- High temperature resistant
- Elastomeric
- Tough
- General purpose
- Medical

Users can work with any material using the OpenAM™ software. Open materials are:

- Printable on the Origin platform
- Come with instructions and calibration parts guiding the user on how to develop own profiles.
- Other information can be found by contacting the material provider

More information on the OpenAM software and materials can be found further in this document.

| | Preferred | Validated | Open |
|--------------------------------|-----------|-----------|-------------------------------|
| Green profile | | | Provided by material supplier |
| • EcDp | ✓ | ✓ | |
| • Cleaning optimization | | | |
| • Cure optimizatio | | | |
| XY and Z scale factors | ✓ | ✓ | |
| Edge compensation | ✓ | ✓ | |
| MPG | ✓ | | |
| TDS | ✓ | | |
| Print quality testing | | | |
| • Repeatability | ✓ | | |
| • Printability | | | |
| • Accuracy | | | |
| Application-specific profiles | ✓ | | |
| Sold by Stratasys | ✓ | varies | |
| Technical support by Stratasys | ✓ | ✓ | |



High-Temperature-Resistant Materials

Many applications across industries require materials to have high resistance to breaking down or deforming at high temperatures. Some key examples include injection/urethane molds, fluid adapters, and electrical connectors.

Special in the Origin portfolio is Loctite 3D 3955™ from Henkel featuring FST certification and UL-94 V0 at 3mm thicknesses. Due to its ability to consistently heat to and maintain the chamber at 60°C, Origin is the only printer that has Blue Card certification with the 3955 FST material.

Note: our definition of a “high temperature resistance material ” as having a HDT greater than 80 °C.

* Most popular with Origin users




| Material | HDT | Elongation at Break | Impact Strength | Water Absorption (24 hour) | Other | Colors | Thermoplastic Analogue |
|-------------------------|--------------------|---------------------|---------------------------|----------------------------|-----------|--------|------------------------|
| Loctite 3D 3955* FST | 300 °C (572 °F) | 2% | 23 J/m (0.43 ft·lb/in) | 0.3% | FST rated | ■ | Ultem, PBT |
| Loctite 3D IND3380™ ESD | 200°C | 2% | 12 J/m (0.22 ft·lb/in) | 0.59 % | | | |
| Loctite 3D IND403™ | 80 °C (176 °F) | 10% | 27 J/m (0.51 ft·lb/in) | 1.8% | - | ■ | Nylon 6/6 |

High-temperature-resistant materials tend to be more brittle in comparison with other classes of materials.

Customers should avoid using high-temperature-resistant materials for applications where impact or risk of dropping is high.

Additionally, these materials tend to have higher moisture resistance which typically leads to better dimensional and long-term property stability.





Elastomeric materials

Rubber-like materials and 3D printing are no obvious combination. The Origin platform is the best option across all polymer technologies – photopolymer or thermoplastic – for handling high viscosity materials and producing accurate elastomeric parts with high performance properties.


Elastomeric materials come in many different flavors based on shore hardness, resilience, modulus, and other properties to cater to support and enable the specific application. Origin provides users with four elastomeric options – three photopolymers and one silicone - to address applications from sealing to cushioning to specialty compliance use-cases.




| Material | Tear Strength | E Modulus | Elongation at Break | Water Absorption (24 hour) | Shore Hardness | Viscosity | Compliance | Colors | Thermoplastic Analogue |
|---------------------|-----------------------------|----------------------------|---------------------|----------------------------|----------------|-----------|---|--------|------------------------|
| Loctice 3D IND402™ | 28 kN/m (160 lb-F/in) | 42 MPa (0.43 ft-lb/in) | 230% | 3.6% | 85A | 15,000 cP | Irritation ISO 10993-23 | ■ | 85-95A TPU |
| P3™ Silicone 25A | 16 ± 3 kN/m (91 lb F/in) | 1.45 MPa | 672% | 1.5% | 25A | 17,000 cP | Biocompatibility (Cytotoxine ISO 10993-5; Pending) | ■ | Low durometer TPU |
| P3™ Stretch™ IND475 | 7.5 kN/m (43 lb-F/in) | 2.5 MPa (0.28 ft-lb/in) | 122% | 3.2% | 48A | 1,500 cP | Irritation ISO 10993-23 | ■ | Low durometer TPU |
| P3™ Stretch™ 80 | 19 kN/m (108 lb-F/in) | 54 MPa (0.51 ft-lb/in) | 117% | 2.1% | 80-85A | 500 cP | | ■ | 80-90A TPU |



Elastomeric materials



Higher Young's Modulus values indicate that the material is stiffer and has a higher Shore Hardness value. Elastomers with higher stiffness are generally more resistant to tearing.



A stress-strain curve of Loctite 3D IND402 and P3 Stretch IND475 show their difference in physical behavior. Loctite 3D IND402 shows high initial resistance to stretching meaning it is more resilient and has more "springiness." P3 Stretch IND475 shows low resistance until breakage indicating it is a softer-touch material.



Tough Materials

A material's toughness can be described using a variety of different properties and parameters. Our definition of a "tough material" is generally having an impact strength greater than 50 J/m.

Many applications across various industries require tough materials to withstand impact, like a jig being dropped onto the floor, or repetitive motions, like a latch which opens and closes repeatedly. Other example applications where tough materials would be a good choice include housings and industrial adapters or shims.


Unique to our portfolio is Stratasys Dura™ 56 – a high performing material exclusive to Origin and positioned at a more cost-effective price point.



| Material | Impact Strength | E Modulus | Elongation at Break | HDT | Moisture Absorption | Viscosity | Colors | Thermoplastic Analogue |
|--------------------|---------------------------|-----------------------|---------------------|-------------------|---------------------|-----------|--------|-------------------------------|
| Loctite 3D 3843 | 59 J/m (1.11 ft·lb/in) | 1750 MPa (254 ksi) | 44% | 63 °C (145 °F) | 2.0% | 800 cP | ■ ▨ □ | ABS |
| Loctite 3D 3172™ | 73 J/m (1.37 ft·lb/in) | 1500 MPa (218 ksi) | 100% | 52 °C (124 °F) | 1.7% | 1850 cP | ■ ▨ | Impact modified polypropylene |
| Loctite 3D IND405™ | 72 J/m (1.35 ft·lb/in) | 1434 MPa (208 ksi) | 96% | 53 °C (129 °F) | 1.0% | 2300 cP | □ | Impact modified polypropylene |
| P3™ Dura56 | 56 J/m (1.05 ft·lb/in) | 1600 MPa (232 ksi) | 78% | 52 °C (126 °F) | 3.0% | 920 cP | ■ | ABS |




Tough Materials



Origin has a robust portfolio of tough materials featuring different colors, performance profiles, and cost points. The three materials shown above are good choices for parts and applications in high impact environments (manufacturing jigs) or frequently opened and closed (latches).

There is a general rule of thumb regarding temperature resistance and brittleness or toughness: high-temperature-resistant materials tend to be more brittle, and more elastic or tough materials tend to have lower temperature resistance. This should be kept in mind when determining the material best suited for your application.





General Purpose Materials

General purpose materials are recommended for applications that require good, all-around performance, are easy to print and process, or both. New and experienced users prefer them for their ease of printing as well as wide applicability across diverse use-cases. That makes these materials also a good choice for initial testing and for applications with relatively low requirements.

Noteworthy in this group is Somos® WeatherX 100 – a proven, high-performing material combining best-in-class UV resistance and improved chemical resistance with very low moisture absorption.

Ultracur3D® ST45 is an easy-to-use, high performing, and cost-effective material option.



Somos WeatherX 100 has been our go-to option for a lot of the miscellaneous components”

Major Automotive OEM partner


| Material | Impact Strength | E Modulus | Elongation at Break | Moisture Absorption | HDT | Viscosity | Colors | Thermoplastic Analogue |
|---------------------|---------------------------|-----------------------|---------------------|---------------------|-------------------|-----------|--------|------------------------------|
| Somos® WeatherX 100 | 27 J/m (0.51 ft-lb/in) | 1943 MPa (282 ksi) | 19% | 0.4% | 73 °C (163 °F) | 950 cP | ■ | UV-stabilized thermoplastics |
| Ultracur3D ST45 | 30 J/m (0.56 ft-lb/in) | 2000 MPa (290 ksi) | 21% | 5.0% | 63 °C (145 °F) | 320 cP | ■ □ | ABS |

General Purpose Materials

The products shown here are easy-to-use and high performing materials.

Consider Somos WeatherX 100 for any applications exposed to higher levels of UV, water, or extended periods of elevated temperature.

ST45 is very easy and fast to print – great for initial part testing.





Medical Materials

Additive manufacturing has many applications within the medical industry, taking advantage of the ability to rapidly test and produce customer parts for patient-specific fits or for medical device testing.


Origin's portfolio contains two medical-specific materials – Loctite 3D MED412™ and Loctite 3D MED413™, both with ISO 10993-5/10/22 approvals – capable of meeting requirements for medical device equipment components, orthotics/prosthetics, and other applications.

Future materials in development focus on improving and increasing the number of sterilization cycles the part can withstand for repeated usage.



| Material | Impact Strength | E Modulus | Elongation at Break | Moisture Absorption | HDT | Colors | Thermoplastic Analogue |
|-------------------|---------------------------|-----------------------|---------------------|---------------------|-------------------|--------|-------------------------------|
| Loctite 3D MED412 | 50 J/m (0.94 ft-lb/in) | 1300 MPa (189 ksi) | 110% | 0.27% | 40 °C (104 °F) | □ | Impact modified polypropylene |
| Loctite 3D MED413 | 27 J/m (1.12 ft-lb/in) | 1600 MPa (232 ksi) | 50% | 2.7% | 70 °C (158 °F) | □ ▨ | UV-stabilized thermoplastics |

Medical Materials



Origin features two medical-specific materials in our portfolio.

Consider Loctite® 3D MED413 for applications and parts requiring higher temperature resistance and stiffness such as surgical guides and medical device components.

Loctite® 3D MED412 is a good option for applications requiring very low water absorption and high toughness, like nasal swabs, catheter tips, and single-use medical devices.



What are Open Materials?

Open materials include materials that bring unique material properties. They complement Stratasys' Preferred and Validated materials portfolio by enabling new and advanced applications.

Open Materials for Origin are available to end-users who purchased OpenAM™ software. Once the OpenAM software is purchased, the pre-made material profiles are immediately available in the Origin software and ready for printing. Although Origin users are free to print any material, the intention of having pre-made profiles is to simplify and accelerate the process of creating a profile and begin printing.

OpenAM software

The OpenAM software provides greater control over the printing process by expanding the list of changeable print parameters. OpenAM software users are given a one-time training on how to use the tool and have expanded coverage for non-certified material on the service contract.

OpenAM software users can run any material they want with the software, including materials not on the Open Materials list, like materials developed in-house.

The standard Origin warranty for the printer itself remains in place, also under use with Open Materials.

Open Materials vs Preferred and Validated Materials

- Pre-made profiles were developed by the material supplier based on their recommendations and experience. Stratasys did not perform additional testing nor did it align these profiles to any specific standard.
- Profiles may change and improve over time based on the material supplier's request.
- The material supplier is responsible for ensuring all required documentation and setup is available for interested end users. This includes SDSs, TDSs, regulatory compliance, material stocking, and so on.
- Open Materials may have additional or different design considerations, workflows, and post-processing steps. OpenAM users are encouraged to contact material suppliers for support and conduct their own internal testing to determine optimal settings and workflows.
- OpenAM users can reach out to the material suppliers and their resellers directly. These materials are not stored or distributed by Stratasys.
- Stratasys only provides benchmark parts and support for preferred and validated materials, not for parts in Open Materials. Please contact the material supplier for benchmarking material requests.



Open Materials List – For use with OpenAM™ software

| Material name | Description | Ultimate tensile strength | Elongation at break | Tensile modulus | HDT | Notched Izod impact | Hardness | Colors | Consider replacing | Supplier | Spec Sheet |
|-----------------|--------------------------|---------------------------|---------------------|-----------------|---------|---------------------|----------|--------------|---|------------|-------------------------------------|
| RG 1100 B | High temp | 70 Mpa | 5% | 2950 | 100°C | 21 J/m | 84D | Black | Nylon 6, PBT | Forward AM | Forward AM |
| RG 1100 | High temp | 70 Mpa | 5% | 3080 | 116°C | 16 J/m | 85D | Clear | Nylon 6, PBT | Forward AM | Forward AM |
| IND147 | High temp | 67 MPa | 2% | 3190 Mpa | 290°C | 14.6 J/m | 94 D | Black | PEEK | Henkel | LOCTITE AM |
| IND249 | High temp | 98 MPa | 5% | 3300 Mpa | 115°C | 24 J/m | 88 D | Black | Nylon 6 | Henkel | LOCTITE AM |
| IND406 | High temp | 55 MPa | 25% | 1600 Mpa | 107°C | 40 J/m | 79 D | Black | 3D printed Nylon 12 | Henkel | LOCTITE AM |
| N3D-HT511 | High temp | 54 Mpa | 7% | 2400 Mpa | 130°C | — | — | Black | Nylon 6, PBT | Sartomer | Sartomer |
| N3D-FR512 | High temp, FR rating | 42 Mpa | 4% | 5100 Mpa | 170°C | — | — | — | FR engineering plastic, Nylon 6, PBT | | Sartomer |
| RG 9400 B FR | High temp, FR rating | 78 Mpa | 3% | 3900 | 255°C | 20 J/m | 88D | Black | FR engineering plastic, Nylon 6, PBT | Forward AM | Forward AM |
| Formula One | ESD; High stiffness | 95 MPa | 5.3% | 3300 MPa | — | 22 J/m | 88 D | Black | Static ESD materials | Mechnano | Mechnano F1 |
| C-Lite | ESD; High temp | 64.7 MPa | 3.2% | 2300 MPa | 250 °C | 22 J/m | — | Black | High Temp ESD materials | Tethon 3D | Contact Tethon3D |
| Bison Porcelite | Specialty; Ceramic | — | — | — | 1200 °C | — | — | — | Aluminum silicate | Tethon 3D | Contact Tethon3D |
| Castalite | Specialty; I.C. shells | — | — | — | 1200 °C | — | — | — | Investment Casting Pattern | Tethon 3D | Castalite Guideline |
| CAST 245 | Specialty; I.C. patterns | 900 MPa | 4% | 12.5 MPa | — | — | — | Purple | Investment Casting Material | Arkema | Arkema N3D-CAST245 |
| RG 3280 | Specialty; High temp | 87 Mpa | 1.3% | 10600 | 284°C | 24 J/m | 96D | Natural | IM metal insert with ISO10993-5 | Forward AM | Forward AM |
| N3D-TOUGH784 | Tough | 50 Mpa | 45% | 2020 Mpa | 56°C | -- | -- | Black | ABS | Sartomer | Sartomer |
| IND6845 | Tough | 48 MPa | 40% | 2100 Mpa | 80°C | 30 J/m | 82D | | ABS | Henkel | LOCTITE AM |
| ST 7500 G | Tough | 54 Mpa | 13% | 2300 Mpa | 54°C | 25 J/m | 82 D | — | ABS | Forward AM | Forward AM |
| IND5714 | Elastomer | 3 MPa | 143% | 4.9 MPa | — | — | 53 A | Grey | Low durometer TPU | Henkel | LOCTITE AM |
| FL 300 | Elastomer | 5 Mpa | 245% | — | — | — | 40 A | Clear | Low durometer TPU/ silicon with ISO10993-5 and ISO10993-10 | Forward AM | Forward AM |
| EL 60 | Elastomer | 9 Mpa | 95% | — | — | — | 75 A | Clear | High durometer TPU/ silicon with ISO10993-5 and ISO10993-10 | Forward AM | Forward AM |
| MED414 | Medical; Elastomer | 4 MPa | 240% | 4 MPa | — | — | 51 A | Blue | Low durometer medical TPU | Henkel | LOCTITE AM |
| MED9851 | Medical, High stiffness | 45 MPa | 40% | 2300 Mpa | 68°C | 50 J/m | 81 D | clear | Medical ABS | Henkel | LOCTITE AM |
| MED3394 | Medical; High temp | 76 MPa | 14% | 2300 MPa | 100°C | 26 J/m | 75 D | Black, White | Sterilizable products | Henkel | LOCTITE AM |
| PRO410 | General purpose | 48 MPa | 5% | 1900 Mpa | 76°C | 28 J/m | 84 D | Black | Prototyping parts | Henkel | LOCTITE AM |
| PRO417 | General purpose | 40 MPa | 100% | 1300 Mpa | 49°C | 54 J/m | 73 D | Black | Polypropylene | Henkel | LOCTITE AM |
| PRO476 | General purpose | 42 MPa | 60% | 1700 Mpa | 62°C | 45 J/m | 78 D | Black | Polypropylene | Henkel | LOCTITE AM |
| PRO9274 | General purpose | 33 MPa | 7% | 1500 Mpa | 52°C | 26 J/m | 80 D | Grey | Prototyping parts | Henkel | LOCTITE AM |
| N3D-PR184-BIO | General purpose; bio | 32 Mpa | 7% | 1970 Mpa | 81°C | — | — | — | Prototyping parts | Sartomer | Sartomer |



Open Materials List – For use with OpenAM™ software

| Material name | Description | Ultimate tensile strength | Elongation at break | Tensile modulus | HDT | Notched Izod impact | Hardness | Colors | Consider replacing | Supplier | Spec Sheet |
|---------------|-----------------|---------------------------|---------------------|-----------------|-------|---------------------|----------|--------|--|------------|------------------------------------|
| ST 7500 G | General purpose | 54 Mpa | 13% | 2300 Mpa | 64°C | 25 J/m | 82 D | Grey | ABS, delrin with ISO10993-5 and ISO10993-10 | Forward AM | Forward AM |
| RG 35 B | Rigid | 62 Mpa | 10% | 2600 Mpa | 87°C | 21 J/m | 83 D | Black | Nylon 6, PBT with ISO10993-5 | Forward AM | Forward AM |
| RG 35 | Rigid | 80 Mpa | 6% | 2600 Mpa | 83°C | 23 J/m | 85 D | Clear | Nylon 6, PBT with ISO10993-5 and ISO10993-10 | Forward AM | Forward AM |
| Strong-X | High stiffness | 84 MPa | 6% | 3500 MPa | 73 °C | 17 J/m | 90 D | Grey | Nylon 6, PBT | Liqcreate | Liqcreate Strong-X |



stratasys.com
ISO 9001:2015
Certified

Stratasys Headquarters
5995 Opus Parkway,
Minnetonka, MN 55343
+1 800 801 6491 (US Toll Free)
+1 952 937-3000 (Intl)
+1 952 937-0070 (Fax)

1 Holtzman St., Science Park,
PO Box 2496
Rehovot 76124, Israel
+972 74 745 4000
+972 74 745 5000 (Fax)

MATERIAL GUIDE P3™ DLP

© 2025 Stratasys Ltd. All rights reserved. Stratasys, Stratasys signet, Origin, P3, Deflect, Dura, Somos, Stretch, WeatherX, are trademarks or registered trademarks of Stratasys Ltd. and/or its subsidiaries or affiliates and may be registered in certain jurisdictions. All other trademarks belong to their respective owners. Product specifications subject to change without notice. MG_P3_Materials Overview_A4_0725a